



TENAGA KIMIA SENDIRIAN BERHAD (26191A)

Administration & Sales Office

Address: No. 8, Jalan SS 22/21, Damansara Jaya,
47400 Petaling Jaya, Selangor
Tel: + 60 - 3 - 7729 7464
Fax: + 60 - 3 - 7729 8383
E-mail: sales@tenagakimia.com

Factory

Address: Lot 5065, 48100 Batu Arang,
Selangor, Malaysia
Tel: + 60 - 3 - 6035 2801
Fax: + 60 - 3 - 6035 2802
E-mail: plant@tenagakimia.com

Website: <http://www.tenagakimia.com>

TECHNICAL DATA SHEET

PRODUCT: EMULSION HIGH EXPLOSIVE (CARTRIDGED)
BRAND: EMULEX®
SERIES: EMULEX® 700
SIZE (mm): 60

Product Specification

Grade / Series	Density (g/cc)	Detonation Velocity (m/s)*	Explosion Energy (MJ/kg)**	Bulk Strength (% Rel ANFO)	Water Resistance	Cap Sensitive	Fume Class
Emulex® 700	1.15 - 1.20	5,000 - 5,500	3.00	117	Excellent	Standard seismic detonator	1

* VOD of product is dependent on product properties and diameter design.

** Energy value is calculated using a special design program. Calculation based on thermodynamic properties.

Shelf Life

TK cartridged emulsion products have a recommended shelf life of 1 year when stored in a clean, dry, cool and well-ventilated magazine.

Sleep Time

TK cartridged emulsion products' sleep time will be subjected to the recommended sleep time of the blasting agents or initiation systems that are used.

Temperature Requirement

TK cartridged emulsion products functioned well in temperatures ranging from 0° to 50° C.



Package Specification

Grade / Series	Dimension Size (mm)	Type of Cartridge	Cartridge Weight (Approx. kg)	Case Weight (Approx. kg)
Emulex® 700	60 x 180	ABS canister	0.5	20
	60 x 354	ABS canister	0.10	16

Disclaimer

Information, data and suggestions given here are based on our best knowledge and believe to be true and accurate. Please read all statements here in conjunction with our condition of sale of goods and services. We assume no responsibility for the use of these statements, data and recommendation and do not suggest any violation of any patent or copyright by its usage.